

SILICONE PASTE

PUTTY TECH FOR MICROCASTING

CHARACTERISTICS

1. High viscosity
2. High hardness
3. Excellent mechanical resistance
4. Suitable for various processes

PASTA SILICONICA

PUTTY TECH PER MICROFUSIONE

CARATTERISTICHE

1. Elevata viscosità
2. Elevata durezza
3. Ottima resistenza meccanica
4. Adatta per molteplici lavorazioni

OPERATING INSTRUCTIONS

Weigh the two components in equal parts, with a ratio of 1:1. (Example: 100 g comp. A + 100 g comp. B).
Mix the two components for approximately 1 minute until a totally homogeneous mixture is obtained.
Pour the mixture into the specific mould.

ISTRUZIONI D'USO

Pesare i due componenti in parti uguali, con un rapporto di 1:1. (Esempio: 100 g comp. A + 100 g comp. B).
Miscelare i due componenti per circa 1 minuto fino a ottenere un composto totalmente omogeneo.
Versare la miscela nell'apposito stampo.

TECHNICAL DATA DATI TECNICI

Hardness	Durezza	60 Sh-A
Gel time	Tempo di utilizzo	90 sec
Hardening time	Tempo d'indurimento	5 min (25°C 77 F°)

The PUTTY TECH silicone paste is available in packs of 1 kg / component.
(codes 36101155 component A, 36101156 component B)

La pasta siliconica bicomponente PUTTY TECH è disponibile in confezioni da 1 kg / componente.
(codici 36101155 componente A, 36101156 componente B)